

Sieve Analysis as per ASTM D 5644

Product: TTII PRO-MAX 37F TPE Infill
Source: St. Hubert, QC
Colour: Green

Technician: Gaylene Bennett
Date Tested: April 24, 2015
Date Received: April 24, 2015

Free Fiber Content ASTM D 5603: 0.00%
mass, grams: 0

Density ASTM D 5603: 618.7 kg/m³
38.6 lb/ft³

Initial Sample Weight (g): 100.0
Talc Weight (g): 5.0

					Specification	
ASTM E-11 Sieve No.	ISO 3310-1 Sieve (mm)	Weight Retained [g]	Individual % Retention	Cumulative % Passing	Minimum % Retention	Maximum % Retention
10	1.00	1.4	1.4	98.6		
12	1.70	3.5	3.5	95.1		
16	1.18	43.8	43.5	51.6		
20	0.850	36.2	36.0	15.6		
30	0.600	12.9	12.8	2.8		
40	0.425	2.2	2.2	0.6		
Pan		0.6	0.6	0.0		
Total		100.6	100.0			



