

Sieve Analysis as per ASTM D 5644

Product: TTII PRO-MAX 37 TPE
Source: St. Hubert, QC
Colour: Green

Technician: Marcella Dauncey
Date Tested: October 31, 2014
Date Received: October 31, 2014

Free Fiber Content ASTM D 5603: 0.00%
mass, grams: 0

Density ASTM D 5603: 0.75 g/cm³
 46.8 lb/ft³

Initial Sample Weight (g): 100.0
 Talc Weight (g): 5.0

					Specification	
ASTM E-11 Sieve No.	ISO 3310-1 Sieve (mm)	Weight Retained [g]	Individual % Retention	Cumulative % Passing	Minimum % Retention	Maximum % Retention
8	2.36	0.0	0.0%	100.0%		
10	2.00	39.4	38.8%	61.2%		
12	1.70	51.3	50.5%	10.7%		
16	1.18	10.3	10.1%	0.6%		
20	0.90	0.5	0.5%	0.1%		
30	0.60	0.0	0.0%	0.1%		
40	0.425	0.0	0.0%	0.1%		
Pan		0.1	0.1%	0.0%		
Total		101.6	100.0			

