

Product: 8-14 COOL-LITE Zeolite
Location: Winston, NM
Technician: Lynne Prostran

Date Received: April 21, 2018
Date Tested: April 24, 2018

Initial Sample Weight (g): 241.6

ASTM E-11 Sieve No.	Weight Retained [g]	Individual % Retained	Cumulative % Passing	Specification	
				Minimum % Passing	Maximum % Passing
6	0.0	0.0%	100.0%		
8	2.4	1.0%	99.0%		
12	133.0	55.2%	43.8%		
14	54.4	22.6%	21.2%		
16	31.5	13.1%	8.2%		
18	13.1	5.4%	2.7%		
Pan	6.6	2.7%	0.0%		
Total	241.0	100.0%			



