



Fine 70-100



Medium 40-70



Medium/Coarse 20-40



Coarse 10-40

SPECIFIC GRAVITY	2.50
DENSITY	Approx. 80 lbs/cu. ft.
HARDNESS	Approx. 6.0 (Mohs)
CHLORIDES	<0.0002%
EMBEDMENT AT 100 PSI	0.0% to 0.4%
SHAPE	Angular to sub-angular
LOI	0.08%
SOFTENING POINT	Approx. 1,350°F

TYPICAL COMPOSITION

SiO ₂	73%	MgO.....	<1%
Na ₂ O.....	14%	Al ₂ O ₃	<1%
CaO	10%	SO ₃	<1%